

Formulation Example

MSAS.1008.01.08.19 Natural Eyeshadow Balm

Ingredients

A

Colorona® Bronze Fine

Colorona® Tangerine Orange

RonaFlair® Flawless

RonaFlair® White Sapphire

RonaFlair® Softshade

INCI (US)

[%]

(1) MICA (AND) IRON OXIDES	19.65
(1) MICA (AND) IRON OXIDES (AND) TITANIUM DIOXIDE	19.65
(1) SILICA (AND) TITANIUM DIOXIDE (AND) IRON OXIDES	14.40
(1) ALUMINA (OR ALTERNATIVELY: SYNTHETIC SAPPHIRE)	3.50
(1) TITANIUM DIOXIDE (AND) MICA (AND) SILICA (AND) ALUMINA	3.50

B

2225 Phyto Wax

Biophilic H

Emogreen™ L15

Cetiol CC

Cetiol® C5

(2) HELIANTHUS ANNUUS (SUNFLOWER) SEED WAX (AND) OLEA EUROPAEA (OLIVE) OIL UNSAPONIFIABLES (AND) RHUS VERNICIFLUA PEEL WAX/RHUS SUCCEDANEA FRUIT WAX (AND) SHOREA ROBUSTA RESIN	4.40
(3) PALMITIC ACID (AND) HYDROGENATED LECITHIN (AND) C12-16 ALCOHOLS	2.20
(4) C15-19 ALKANE	13.00
(5) DICAPRYLYL CARBONATE (AND) TOCOPHEROL	12.70
(5) COCO-CAPRYLATE (AND) TOCOPHEROL	7.00

Procedure:

Prepare phase B and heat it to 80°C. Add slowly phase A and mix until all pigments and fillers are well dispersed. At 80°C, pour the paste into suitable packaging and let it cool down to room temperature.

Notes:

Appearance : golden bronze thick balm

Stability : 3 months at room temperature, 4°C and 45°C

All ingredients referring to INCI are available as COSMOS approved raw materials.

Suppliers:

(1) Merck KGaA, Darmstadt, Germany / EMD Performance Materials

(3) Lucas Meyer GmbH & Co. KG

(5) BASF AG

(2) Kahl GmbH & Co. KG

(4) Seppic

□

Products are warranted to meet the specifications set forth on their label/package and/or certificate of analysis at the time of shipment or for the expressly stated duration. EMD provides information and advice on application technologies and relevant regulations based upon its current knowledge and opinion. EMD MAKES NO REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE REGARDING OUR PRODUCTS, THEIR APPLICATION OR ANY INFORMATION PROVIDED IN CONNECTION THEREWITH. EMD shall not in any event be liable for incidental, consequential, indirect, exemplary or special damages of any kind resulting from any use or failure of the products. Customer is responsible for and must independently determine the suitability of EMD's products for its products, intended use and processes. The foregoing information and suggestions are also provided without warranty of non-infringement as to intellectual property rights of third parties and shall not be construed as any inducement to infringe the rights of third parties. Customer shall be responsible for obtaining any applicable third party intellectual property licenses. All sales are subject to EMD's complete Terms and Conditions of Sale. Prices are subject to change without notice. EMD reserves the right to discontinue products without prior notice. EMD, EMD Performance Materials, the vibrant M, Colorona, Timiron, Xirona, RonaFlair, Ronastar, Candurin, Eusolex, Parteck, Oxyxex, RonaCare, IR3535, UV-Pearls, ASCIII, Luremin and Emblicain are trademarks of Merck KGaA, Darmstadt, Germany. All other trademarks pertain to their proprietors. □