



## SPEED OF BLUE

At the Speed of Blue, you see flawless, silky elegance. A digital playground, a formulation suitable for a liquid-effect stylized for outdoor applications. Iriodin® Icy White Pristine delivers...at the speed of blue.

49.25% Iriodin® 96111 Icy White Pristine

0.13% Emperor® 2000

25.22% Microtitan® MT 500HD

1.42% Kronos® 2190

0.52% Hostaperm® Pink E-TS

15.56% Stapa® Hydrolan 2156

7.78% Monolite® Blue 3R

PWC in dry film = 26%



# TECHNICAL DATA

## Base Coat

1-component solvent-borne basecoat  
Applied layer thickness: 12 – 16 µm

## Clear Coat

2K high gloss clear coat  
Applied layer thickness 45 – 55 µm

## Pigmentation

The PWC (Pigment Weight Concentration) in the dry film is indicated for each styling

$$\text{PWC} = p / (p + b)$$

p = total weight pigments (solid)

b = weight binder (solid)

In the dry state: Pigment / binder ratio =  $(\Sigma \text{Pigment}) / (\text{Total solid content (wet form)} - (\Sigma \text{Pigment}))$

## Feasibility for on-line application

The stylings in our color inspirations are intended to demonstrate future effect color directions and possibilities. Although we have tried to make the formulations as realistic as possible, we cannot guarantee their full feasibility for on-line application. A certain degree of modification and fine tuning will probably be necessary.

# THIRD PARTY TRADEMARKS

Emperor® is a trademark of Cabot Corporation, Boston, USA

Microtitan is a product of Tayca Corporation, Osaka, Japan

Kronos® is a trademark of Kronos Worldwide Inc., Dallas, USA

Hostaperm® is a trademark of Clariant International Ltd, Muttenz, Switzerland

Monolite® is a trademark of Heubach GmbH, Langelsheim, Germany

Products are warranted to meet the specifications set forth on their label/packaging and/or certificate of analysis at the time of shipment or for the expressly stated duration. EMD Performance Materials Corp. provides information and advice on application technologies and relevant regulations based upon its current knowledge and opinion. EMD PERFORMANCE MATERIALS CORP. MAKES NO REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE REGARDING OUR PRODUCTS, THEIR APPLICATION OR ANY INFORMATION PROVIDED IN CONNECTION THEREWITH. EMD Performance Materials Corp. shall not in any event be liable for incidental, consequential, indirect, exemplary or special damages of any kind resulting from any use or failure of the products. Customer is responsible for and must independently determine the suitability of our products for its intended use and processes. The foregoing information and suggestions are also provided without warranty of non-infringement as to intellectual property rights of third parties and shall not be construed as any inducement to infringe the rights of third parties. Customer shall be responsible for obtaining any applicable third party intellectual property licenses. All sales are subject to our complete Terms and Conditions of Sale. Prices are subject to change without notice. EMD Performance Materials Corp. reserves the right to discontinue products without prior notice.

© 2023 Merck KGaA, Darmstadt, Germany and/or its affiliates. EMD Electronics, the vibrant M, and Iriodin are trademarks of Merck KGaA, Darmstadt, Germany or its affiliates. All other trademarks are the property of their respective owners. Detailed information on trademarks is available via publicly assessable resources.